

## Pressure-Resistant Gap Balancing Systems



### Viaduct Altwipfelgrund 2004

Installing bridge bearings with MM 1018 to positively fill the gaps between bottom plates and bridge bearing plates.



### Waterway crossing Magdeburg 2003

Positive ties of the gaps between bottom plates and bridge bearing plates using MM 1018.



### Range

DIAMANT MM 1018 is available in the following types:

- MM 1018 P # 2044 paste-like / spreading with a float
- MM 1018 FI # 2060 liquid / pour or inject
- MM 1018 P slow # 2041 paste-like / spreading with a float

### Shelf Life

min. 12 month

### Pack Sizes (cpl.)

twin pack:

1,5 kg ~ 600 ccm

4,5 kg ~ 1.800 ccm

special sizes on request



### Typical Applications

- fitting from bridge bearings
- gap balance at face plates from steel constructions
- relining from support columns, rails and presses
- slide rails at flood gates
- relining from wedge plates and chuck plates at new buildings

### Product Description

DIAMANT MM 1018 is a highly loadable metal polymer to produce a form- and force-fitted gap balance at steel constructions. The material has a high pressure resistance, also under extreme conditions like vibrations or thermal fluctuations from -40°C to +90°C, and is, next to its weathering resistance, mainly characterized by its easy handling (machining) and trouble-free application.

### Properties

- ◆ 100% gap balance from 0 - 10 mm, NO SHRINKAGE
- ◆ high comprehensive strength
- ◆ absorbing vibrations
- ◆ temperature-resistant from -40 °C to +90 °C
- ◆ weather-proof
- ◆ corrosion-resistant
- ◆ non-conducting
- ◆ resistant to fuel, oil, coolant and environmental influences
- ◆ easy and problem-free application on the spot without specific preparations and tools

### Accessories & Services

DIAMANT Separating Agent liquid # 1354 or spray # 1355

DIAMANT Safety Cleaner liquid # 1417 or spray # 1534

Injection equipment:

- injection pipe
- unidirectional valves
- hand injection gun
- cartridges
- mixing propeller



We also offer a comprehensive product and process design service

to optimise the usage in special applications.

Our experienced technicians like to advise you in all questions around the application of our products.



Over 600 applications worldwide!!

On request you can have our extensive list of references.

Product application by specialised firms!

On demand our Diamant Service Team will take over the application for you. We are looking forward to make an appointment with you.

All material values are average values and vary due to material quantity and environmental conditions. The mentioned material values are based on normal conditions (STP) of 20°C (273K / 31,73°F) and 1013mbar (1013hPa).



channel bridge Lippe 2006



chuck plates being coated with MM 1018




8 - 10 mm gap balance



## Pressure-Resistant Gap Balancing Systems

MM 1018		P #2044	FL #2060	P slow #2041
Pot Life (+20 °C) [min]		45	120	100
Cure Time (+20°C) [h]		24	36	36
Max. Compressive Strength [N/mm <sup>2</sup> ]		160	140	140
E-Modulus DIN 53457 [N/mm <sup>2</sup> ]		14000	12000	14000
Specific Weight [g/cm <sup>3</sup> ]		2,4	2,4	2,6
Tensile Strength [N/mm <sup>2</sup> ]		76	71	76
Bending Strength [N/mm <sup>2</sup> ]		89	83	89
Linear Coefficient of Expansion [1/K]		32 x 10 <sup>-6</sup>	32 x 10 <sup>-6</sup>	32 x 10 <sup>-6</sup>
Static Coefficient of Friction		> 0,5 (see sep. test report)		
Resistance to Chemical		very good (see sep. list)		
Temperature Resistance Permanent [°C]		-40 bis +90	-40 bis +90	-40 bis +90
Mixing Ratio by Weight	Komp. (A)	7,9	9,6	8,3
	Komp. (B)	2,1	0,4	1,7



### Preparation

Roughen adhesion areas and clean chemically (optimum: **DIAMANT** cleaner), degrease and if necessary apply **DIAMANT** separator. Seal screw holes so that **MM 1018** will not paste over the screwing while fitting the bearings. At relining cavities the surrounding gap has to be sealed by pressing in **MM 1018 P** or by welding on some steel strips. There also have to be applied some adequate injection and ventilation holes.

### Application

#### Paste-like

To begin immediately with the assembly after the application from **MM 1018 P** the bearings should be brought into the right position directly from the beginning of the application. Pour the hardener (comp. B) fully into the resin (comp. A) container. Mix by machine with propeller mixer (250 rpm for ca. 2 min.). Mix until the hardener has mixed well into the tougher resin. Ensure that all the material is removed from the walls and sides of the tin and is mixed properly. Apply the whole calculated mass of **MM 1018 P** roof like. Assemble the bearing immediately. Remove excess material before curing by spatula.

#### Liquid

After mixing (see above) pour **MM 1018 FL** into an empty cartridge and push the piston in. Turn the cartridge slowly around 180° so that the air can rise to the top of the cartridge. Cut off the top of the cartridge, attach the nozzle, put into hand injection gun and insert into the injection hole. Inject **MM 1018 FL** slowly into the gap until the material leaks out of the ventilation hole. After finishing the injection all holes have to be closed with plugs or valves.

The material has a curing time from 24 (**MM 1018 P**) and respectively 36 (**MM 1018 FL**) hours at 20°C.